



Att Mr George Naguib
M/s Feltex Carpets Pty Ltd,
35-65 Paramount Rd, Melbourne 3012

TEST REPORT No. 082993

LABORATORY REF: P082993A

CUSTOMER REFERENCE

KNIGHTS POINT

Sample description as provided by customer

Order No. FTX1004

Mass/unit area 20 oz/yd² g/m² Pile Fibre Content 90% SOLUTION DYED NYLON 10% SPACE DYED NYLON

Construction Details Tufted Secondary Backing Jute
Style LOOP

Colour Blue
Pile Height / mm

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10a of the Building Code of Australia.

Tested in accordance with the Carpet Institute Code of Practice for AS/ISO 9239 Testing Version 10 / 0805.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. Clause 9 of AS/ISO 9239 Part 1

Conditioning as specified in BS EN 13238.2001

Sample submitted Date 25/11/2008

Test Date 8/12/2008

ASSEMBLY SYSTEM DOUBLE BOND (DOUBLE STICK) details below.

The underlay used was SENSI SLAB it was adhered to the substrate using ROBERTS 656 adhesive. The floor covering was adhered to the underlay using ROBERTS 95 adhesive.

Substrate : Non-combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.
Sample Cleaned as Specified in ISO 11379.1997

Initial Test Specimen 1 Length Direction Critical Radiant Flux 1.6 kW/m²
Specimen 1 Width Direction Critical Radiant Flux 1.5 kW/m²
Full tests carried out in the Width Direction




SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	1.5	1.6	1.6	1.6
Smoke Development Rate (%.min)	470	459	435	455

The values quoted below are as required by Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out.

MEAN CRITICAL RADIANT FLUX 1.6 kW/m²

MEAN SMOKE DEVELOPMENT RATE 455 %.min

OBSERVATIONS The samples shrunk away from the heat source then ignited

 ACCREDITED FOR TECHNICAL COMPETENCE	Authorised Signatory M. E. Webb Technical Manager  DATE 
	Measurement Science and Technology No. 15393
	1003.05.07

PAGE 1 of 2

Page 2 only shows the time required in seconds for the flame front to reach each time marker, the total test time and the CHF value at 30 minutes (if applicable).

The laboratory allows the use of this page of the report without the use of page 2.