Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

Client: Gerflor Australasia Pty Ltd

17 Cato Street

Hawthorn East VIC 3123

Test Number : 19-002248

**Issue Date** : 24/07/2019

Print Date : 24/07/2019

Sample Description Clients Ref : "Mipolam Affinity"

Vinyl Sheet

Colour: Brown Speckled

End Use: Commerical Wall Covering

Nominal Composition: PVC

Nominal Mass per Unit Area/Density: 2850 g/m2

Nominal Thickness: 2mm

AS/NZS 3837-1998 Method of Test for Heat and Smoke Release Rates for Materials and Products using an Oxygen

Consumption Calorimeter

Date Tested 23/07/2019

Operator AWTA Test Operator 3

Face Tested Face

Specimen

1 2 3 Mean

Average Heat Release Rate 48.4 45.6 46.5 46.9 kW/m²
Average Specific extinction area 222.3 205.6 225.9 217.9 m²/kg

(according to Specification C1.10 of the Building Code of Australia)

Test orientation: Horizontal

Specimen Mean 1 2 3 50 50 50 50 kW/m<sup>2</sup> Irradiance m³/s 0.024 0.024 0.024 0.024 Exhaust flow rate Time to sustained flaming 20 25 22 22 sec Test duration 834 874 805 838 sec 127.3 134.9 126.3 129.5 kW/m<sup>2</sup> Peak heat release after ignition Average heat at 60 s 106.7 106.9 113.9 109.1 kW/m<sup>2</sup>

104315 35695 Page 1 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

- Mechanical Testing

Performance & Approvals Testing

: Accreditation No. 983 : Accreditation No. 985 : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hone

# **AWTA Product Testing**

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

Gerflor Australasia Pty Ltd Client:

17 Cato Street

Hawthorn East VIC 3123

Test Number : **Issue Date** 

19-002248

24/07/2019

**Print Date** 

24/07/2019

Average heat at 180 s	99.1	98.1	99.8	99.0	kW/m²
Average heat at 300 s	86.2	84.1	84.5	84.9	kW/m²
Total heat released	39.4	38.7	36.4	38.2	MJ/m²
Average effective heat of combustion	10.3	10.3	10.1	10.2	MJ/kg
Initial thickness	8	8	8	8.0	mm
Initial mass	120.6	118.5	120.0	119.7	g
Mass at sustained flaming	120.6	118.4	120.0	119.7	g
Mass remaining	89.8	88.1	90.5	89.5	g
Mass percentage pyrolysed	25.6	25.7	24.6	25.3	%
Mass loss	3.8	3.8	3.6	3.7	kg/m²
Average rate of mass loss	4.7	4.4	4.6	4.6	g/m².s
Additional Observations	None				
Difficulties Encountered during Testing	None				

Tests were conducted with a wire grid placed over the sample during testing. This was done to contain intumescing sample within the sample holder.

These test results relate only to the behaviour of the product under the conditions of the test, they are not intended to be the sole criterion for assessment of performance under real fire conditions.

The results of these fire tests may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of the fire hazard under all fire conditions.

Samples were adhered to a substrate of 6mm thick cement sheet using Roberts 656 wallcovering adhesive prior to testing

104315

35695

Page 2 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

- Mechanical Testing

- Performance & Approvals Testing

Accreditation No 983 Accreditation No. 985 : Accreditation No

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Gerflor Australasia Pty Ltd Client:

17 Cato Street

Hawthorn East VIC 3123

19-002248 Test Number :

Issue Date 24/07/2019


24/07/2019 **Print Date** 

## Specimen:

## Heat release rate (kW/m²) 200 160 120 80 40 200 600 800 1000 Time (s)

# Effective heat of combustion (MJ/kg) 30 20 200 1000 Time (s)

## Smoke production rate ([m²/s]) 0.10 0.08 0.06 0.04 0.02 0.00 200 400 600 800 1000 0 Time (s)



104315

35695

Page 3 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

Mechanical Testing

Performance & Approvals Testing

Accreditation No 983 Accreditation No. 985 Accreditation No 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Gerflor Australasia Pty Ltd Client:


17 Cato Street


Hawthorn East VIC 3123


19-002248 Test Number :


Issue Date 24/07/2019

24/07/2019 **Print Date** 









104315 35695 Page 4 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved

Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

 Mechanical Testing Performance & Approvals Testing Accreditation No Accreditation No. 985 Accreditation No

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



ANAGING DIRECTOR

0204/11/06

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Gerflor Australasia Pty Ltd

17 Cato Street

Hawthorn East VIC 3123


Test Number : 19-002248

Issue Date : 24/07/2019


Print Date : 24/07/2019

## Specimen: 2

# Heat release rate (kW/m²) 160 120 80 40 0 200 400 600 800 1000 Time (s)



# Smoke production rate ([m²/s]) 0.08 0.06 0.04 0.02 0.00 0.00 Time (s)



104315 35695 Page 5 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

Performance & Approvals Testing

: Accreditation No. 983 : Accreditation No. 985 : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Gerflor Australasia Pty Ltd Client:


17 Cato Street


Hawthorn East VIC 3123


19-002248 Test Number :


Issue Date 24/07/2019

24/07/2019 **Print Date** 









104315

35695

Page 6 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

 Mechanical Testing Performance & Approvals Testing Accreditation No Accreditation No.

985 Accreditation No

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Gerflor Australasia Pty Ltd Client:

17 Cato Street

Hawthorn East VIC 3123

19-002248 Test Number :


Issue Date 24/07/2019

24/07/2019 **Print Date** 


### 3 Specimen:

## Heat release rate (kW/m²) 200 160 120 80 40 100 200 400 500 600 700 800 900 Time (s)


## Effective heat of combustion (MJ/kg)



## Smoke production rate ([m²/s])



Specific extinction area (m²/kg)



104315

Australian Wool testing Authority Ltd Copyright - All Rights Reserved

35695

- Accredited for compliance with ISO/IEC 17025 Testing - Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing
- Accreditation No

Accreditation No. 985 Accreditation No

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Page 7 of 8

ANAGING DIRECTOR

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client: Gerflor Australasia Pty Ltd


17 Cato Street


Hawthorn East VIC 3123


Test Number : 19-002248


**Issue Date** : 24/07/2019

**Print Date** : 24/07/2019









104315 35695

Page 8 of 8

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing

- Mechanical Testing

Performance & Approvals Testing

: Accreditation No. 983 : Accreditation No. 985 : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



MICHAEL A. JACKSON B.Sc.(Hons

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **Group Number Assessment**

(In accordance with AS 5637.1-2015)

This is to confirm that the product as described below has been tested by AWTA Product Testing.

Testing was performed in accordance with AS/NZS 3837-1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.

**Test Sponsor**: Gerflor Australasia Pty Ltd

17 Cato Street

Hawthorn East VIC 3123

Test Number : 19-002248
Issue Date : 24/07/2019

**Print Date** : 24/07/2019

Sponsor Product Clients Ref : "Mipolam Affinity"

Vinyl Sheet

Colour: Brown Speckled

End Use: Commerical Wall Covering

Nominal Composition: PVC

Nominal Mass per Unit Area/Density:

Nominal Thickness: 2mm

2850 g/m2

Product Group Number Classification :

Average Specific Extinction Area: 217.9 m²/kg

9:"

Chris Campbell
Client Relations Manager

35695

The message/document(s) contained in this electronic attachment is intended for the party to which it is addressed and may contain confidential information or be subject to professional privilege. It's transmission is not intended to place the contents into the public domain.