

TARALAY INITIAL COMPACT

 **2m R10 P2**   




16.2 cm


0779 OTTAWA POPLAR




16.6 cm


0518 ESTEREL CHOCOLATE





16.6 cm

0636 ESTEREL BLOND





16.6 cm

0828 HABANA BEIGE



0465 STRADA CIMENT

 COMPACT - 2M sheet without foam backing
Diagram indicates plank width

TARALAY INITIAL COMPACT

www.gerflor.com.au

TARALAY INITIAL COMPACT is a multi-layered vinyl floor covering, available in a 2m wide sheet, with a group T wear rating. The product comprises a compacted backing reinforced with glass fibre. The printed design that is protected by a transparent wear layer (0.70 mm thick). It offers 6 dB sound insulation and an indentation resistance of 0.03 mm. It is treated with ProtecSol®, a UV cured surface treatment, which facilitates ease of maintenance and eradicates the need for acrylic emulsion (metallisation). These products do not contain any heavy metals or CMR 1&2 and are 100% compliant with REACH. The products' emission rate of volatile organic compounds is < 10 µg/m³ (TVOC after 28 days – ISO 16000-6). Taralay Initial Compact 100% recyclable.

INSTALLATION

Installation should be carried out in accordance with local standards and is the responsibility of the installer. The subfloor needs to be hard, smooth, clean and dry prior to laying. Where applicable the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatise for 24 hours prior to installation in a room temperature between 18-24 °C. All seams must be heat welded using Gerflor matching weld rod.

MAINTENANCE

Maintenance should be carried out regularly to retain the appearance and durability of the floor. The floor covering should be maintained with regular sweeping and damp mopping using a neutral cleaner, or auto scrubbing machine using an appropriate pad. Rubber leaves indelible stains on vinyl flooring: do not use mats with rubber backing and replace tubular furniture feet with those made of PVC or polyamide. Place mats of sufficient length at entrances to reduce outside sources of dirt.

To download the full Taralay Initial Compact installation and maintenance guides, visit www.gerflor.com.au

DESCRIPTION

Total thickness	EN 428	mm	2
Wearlayer thickness	EN 429	mm	0.70
Weight	EN 430	g/m ²	2635
Width/Length of sheet	EN 426	cm/lm	200/25

CLASSIFICATION

Norm/product specification	-	-	EN 649
European standard	EN 685	class	34-43
Fire rating	AS ISO 9239	kW/m ² / smoke % per min	7.3 / 175
Electrical resistance	EN 1815	kV	<2
Slip resistance wet pendulum	AS 4586-2013 (Appendix A)	class	P2
Slip resistance oil-wet ramp	AS 4586-2013 (Appendix D)	class	R10

PERFORMANCE

Abrasion resistance	EN 660.2	mm ³	≤2.00
Abrasion group	EN 649	group	T
Dimensional stability	EN 434	%	≤0.40
Residual indentation (requirement)	EN 433	mm	≤0.10
Residual indentation (average value measured)	-	mm	0.03
Impact sound insulation	EN ISO 717-2	dB	6
Castor chair test (Type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105-B02	degree	>6
Chemical products resistance	EN 423	class	OK
Anti-bacterial activity	ISO 22196	-	> 99% Inhibits growth
Surface treatment	-	-	ProtecSol®
TVOC after 28 days	ISO 16000-6	µg/m ³	< 10

CE MARKING

	EN 14041	-	
---	----------	---	---

Gerflor has a policy of continuous product and product data improvement, it reserves the right to change design and specifications without notice.



bre



Gerflor
theflooringgroup

www.gerflor.com.au 1800 060 785