

## ATTAR

Advanced Technology Testing and Research

## ATTAR TEST REPORT NUMBER: 14/8073.4



The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025. Accreditation Number: 2735

17 July 2014

## WET PENDULUM SLIP RESISTANCE

## Job No: M14/8073

Total Pages: 2

Prepared for:	Corflor Australasia Bty Ltd					
	Gerflor Australasia Pty Ltd 17 Cato Street					
	HAWTHORN EAST VIC 3123					
Attention:						
	Jutta Fronert					
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.					
Test Date:	10 July 2014					
Test Specimens, Size &	Artline (Dry Back) vinyl plank, 914x152 mm, 5 off					
Quantity:	tested. Refer to Figure 1.					
Sampling & Direction of Testing:	Sampling conducted by client. Test direction parallel					
	with surface profile.					
Test Personnel:	Sean Lake					
Preparation:	Washed with water and pH Neutral detergent, rinsed					
_	then dried.					
Fixed/Unfixed:	Unfixed.					
Air Temperature:	21°C					
Test Equipment:	Munro Stanley Skid Resistance Tester (Pendulum)					
	Serial Number 0320, Calibrated 16/10/2013.					
Test Standard:	AS 4586: 2013 Slip resistance classification of new					
	pedestrian surface materials – Appendix A.					
Slider Rubber:	Slider 96 Batch No. #54 prepared on P400 & 3µm					
	lapping film.					
Classification Criteria:	Refer to Classification Criteria, attached as Appendix 1.					
	Specimen Number					
British Pendulum Number	1	2	3	4	5	SRV
	42	39	37	37	36	38
<u> Oleasifisation</u>	42	- 39			50	- 30
Classification:	P3					

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

ma

Daniel King BEng (Mats) Hons, Materials and Testing Engineer Approved Signatory

> This report may not be reproduced except in its entirety. Page 1 of 2