

**ATTAR TEST REPORT NUMBER: 14/8054.3**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.  
Accredited for compliance with ISO/IEC 17025.  
Accreditation Number: 2735

14 July 2014

**Total Pages: 2****WET PENDULUM SLIP RESISTANCE**

Job No: M14/8054

<b>Prepared for:</b>	Gerflor Australasia Pty Ltd 17 Cato Street HAWTHORN EAST VIC 3123					
<b>Attention:</b>	Jutta Fronert					
<b>Test Site:</b>	ATTAR, Unit 1, 64 Bridge Road, Keysborough.					
<b>Test Date:</b>	10 July 2014					
<b>Test Specimens, Size &amp; Quantity:</b>	Creation Clic vinyl plank, 1000x176 mm, 5 off tested. Refer to Figure 1.					
<b>Sampling &amp; Direction of Testing:</b>	Sampling conducted by client. Test direction parallel with grain profile.					
<b>Test Personnel:</b>	Sean Lake					
<b>Preparation:</b>	Washed with water and pH Neutral detergent, rinsed then dried.					
<b>Fixed/Unfixed:</b>	Unfixed.					
<b>Air Temperature:</b>	21°C					
<b>Test Equipment:</b>	Munro Stanley Skid Resistance Tester (Pendulum) Serial Number 0320, Calibrated 16/10/2013.					
<b>Test Standard:</b>	AS 4586: 2013 Slip resistance classification of new pedestrian surface materials – Appendix A.					
<b>Slider Rubber:</b>	Slider 96 Batch No. #54 prepared on P400 & 3µm lapping film.					
<b>Classification Criteria:</b>	Refer to Classification Criteria, attached as Appendix 1.					
<b>British Pendulum Number</b>	<b>Specimen Number</b>					<b>SRV</b>
	<b>1</b>	<b>2</b>	<b>3</b>	<b>4</b>	<b>5</b>	
	27	27	28	27	26	27
<b>Classification:</b>	<b>P2</b>					

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

**NOTE:** Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

**ATTAR**

Daniel King BEng (Mats) Hons,  
Materials and Testing Engineer  
Approved Signatory

This report may not be reproduced except in its entirety.

**Page 1 of 2**