


		Standard	Requirement	Unit	Result	Tolerance
DESCRIPTION						
Surface treatment	-	-	-	-	Triple Action ProtecSol®	
Surface complex	-	-	-	-	100% PVC	
Foam backing	-	-	-	-	Vertical Closed cell	
Anti-bacterial & Fungicidal treatment	-	-	-	-	Sanosol®	
Thickness	-	EN 428	-	mm	3.7	± 0.15
Weight	-	EN 430	-	kg/m ²	1.9	± 0.10
Length	-	EN 426	-	lm	16 MAX	-0 / +0.20
Width	-	EN 426	-	lm	1.5	-0 / +0.01
SPORT PROPERTIES						
Sliding coefficient	CEN	EN 13036-4	80-110	-	80-110	
	DIN	DIN 18032	0.4-0.6	-	0.4-0.6	
TECHNICAL CHARACTERISTICS						
Abrasion resistance	CEN	EN ISO 5470-1	≤ 1000	mg	≤ 350	
Brightness	CEN	ISO 2813	≤ 30	-	≤30	
Chemical resistance	CEN	EN 423	-	-	Good	
CLASSIFICATION						
Fire	CEN	EN 13501-1	Cfl-s1	-	Bfl-s1	
Thermal resistance	Fr.	NF X 10021/DIN 52612	≤ 0.15	m ² K/W	0.15	
CE MARKING						
		EN 14904 : 2006	EN 13 501-1		EN ISO 5470-1	
			EN 13 036-4			