

**ATTAR TEST REPORT NUMBER: 14/8073.9**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.  
Accredited for compliance with ISO/IEC 17025.  
Accreditation Number: 2735

17 July 2014

**Total Pages: 2****OIL-WET INCLINING PLATFORM SLIP RESISTANCE**

Job No: M14/8073

<b>Prepared for:</b>	Gerflor Australasia Pty Ltd 17 Cato Street HAWTHORN EAST VIC 3123	
<b>Attention:</b>	Jutta Fronert	
<b>Test Site:</b>	ATTAR, Unit 1, 64 Bridge Road, Keysborough.	
<b>Test Date:</b>	16 July 2014	
<b>Manufacturer:</b>	Gerflor	
<b>Test Specimen, Size &amp; Quantity:</b>	Taralay Premium Comfort (P2) vinyl sheet, 500x1000 mm, 1 off tested. Refer to Figure 1.	
<b>Sampling &amp; Direction of Testing:</b>	Sampling conducted by client. Test direction not applicable.	
<b>Test Personnel:</b>	David Padfield and Marcus Braché	
<b>Preparation:</b>	Washed with water and pH Neutral detergent, rinsed then dried.	
<b>Joint Width:</b>	N/A	
<b>Air Temperature:</b>	22°C	
<b>Test Standard:</b>	AS 4586 - 2013 Slip resistance classification of new pedestrian surface materials – Appendix D.	
<b>Surface Structure :</b>	Smooth	
<b>Test Shoes:</b>	Lupos Picasso	
<b>Classification Criteria:</b> (TABLE 5 in AS 4586 - 2013)	<b>Classification</b>	<b>Angle, degrees</b>
	No Classification	<6
	R9	≥6<10
	R10	≥10<19
	R11	≥19<27
	R12	≥27<35
	R13	≥35
<b>Displacement Space:</b>	Not Measured	
<b>Displacement Space Assessment Group:</b>	N/A	
<b>Corrected Mean Overall Acceptance Angle (rounded down to the nearest degree):</b>	9°	
<b>Classification:</b>	R9	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

**NOTE:** Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

**ATTAR**

Marcus Braché  
Senior Engineering Technician  
Approved Signatory

This report may not be reproduced except in its entirety.