

| DESCRIPTION | | | |
|-----------------------|--------------|-------------------|---|
| Total Thickness | EN 428 | mm | 2.00 +/- 0.15 |
| Stabilization | | | CaZn |
| Density | | g/cm ³ | 1.49 |
| Weight | EN 430 | g/m ² | 2800 +/-200 |
| Panels width | EN 426 | mm | 1300 |
| Panels lengths | EN 426 | mm | 3000 |
| Surface | | | smooth and covered with a film in order to protect the panel until the end of the project |
| CLASSIFICATION | | | |
| Fire reaction | EN 13 501-1 | class | B-s2,d0 |
| | NFP 92 – 507 | class | M1 |
| | BSI | class | 0 |
| | ASTM 84 | class | A |

| PERFORMANCE | | | |
|---|------------|-------------------|-----------------------|
| Chemicals resistance (1) | EN 423 | - | OK |
| | | | Anios compliant |
| | | | H2O2 compliant |
| Decontamination of surface (radionuclide) | ISO 8690 | | excellent |
| anti-bacterial activity (E. coli – S. aureus – MRSA) (2) | JIS Z 2801 | - | > 99% inhibits growth |
| Migration of specific metals | EN12149-A | | <2 |
| Vinyl chloride | EN12149-B | | non detectable |
| Formaldehyde | EN12149-C | | non detectable |
| TVOC emission | EN 16000-6 | after 28 days | < 15µg/m3 |
| Impact resistance | ISO 8256 | KJ/m ² | 443 |
| Impact resistance Charpy +23°C -50% HR | ISO 179-1 | | 53,6 |
| Welding resistance with Gerflor contract vinyl flooring (wearlayer > 0,5mm) | NF-EN 684 | DaN/5cm | >24 |

(1) Charts « stain and marks resistance » available upon request

(2) The implementation of an effective cleaning method is the best defence against infection..