

DESCRIPTION			
Total Thickness	EN 428	mm	2.00 +/- 0.15
Stabilization			CaZn
Density		g/cm ³	1.49
Weight	EN 430	g/m ²	2800 +/-200
Panels width	EN 426	mm	1300
Panels lengths	EN 426	mm	3000
Surface			textured
CLASSIFICATION			
Fire reaction	EN 13 501-1	class	B-s2,d0
	NFP 92 – 507	class	M1
	BSI	class	0
PERFORMANCE			
Chemicals resistance			Anios compliant
			H2O2 compliant
Decontamination of surface (radionuclide)	ISO 8690		excellent
TVOC emission	EN 16000-6	after 28 days	< 15µg/m ³